



Product Information

NEBAR BROWN

General Purpose

Description General Purpose High Quality Jointing.
Nitrile/SBR bonded cork for < 3mm thickness,
Polychloroprene/Nitrile bonded cork for >= 3mm thickness.

Specification Compliance ASEA 1169 5012E - 204
ASTM F104 line call out - below 3 mm F224000M2, 3 mm and above F225000M2

Typical Properties Material tested to procedures as documented in ASTM F104

	< 3 mm thick	≥ 3 mm thick	Test Procedure
Base elastomer	NITRILE/SBR	CR/NITRILE	
Thickness	0.8 to 2.5	3 to 13	
Hardness	65 to 85°	65 to 80°	D1415
Minimum tensile strength (MPa)	1.75	1.75	ASTM F152
Fluid resistance, volume swells			
ASTM 1 72 hours at 100°C	-3 to +10%	0 to +10%	ASTM F146
IRM903 72 hours at 100°C	0 to +25%	+10 to +30%	ASTM F146
FUEL A 22 hours ambient temperatures	-5 to +10%	0 to 15%	ASTM F146
BS148 Transformer Oil 14 days at 90°C	+23.1%	+10%	ASTM F146
Low temperature flexibility	-20°C	-30°C	
Maximum operating temperature in fluids	110°C	110°C	
Compressibility at 2.8 N/mm ²	15 to 25%	20 to 30%	ASTM F 36
Recovery minimum	75%	75%	ASTM F 36
Normal sheet size	1.2 x 1.0 1.2 x 1.2	1.2 x 1.2	
Flexibility	3d	3d	ASTM F 147

Tiflex Limited

Tiflex House, Liskeard, Cornwall, PL14 4NB
Tel : +44 (0)1579 320808
E-mail : sales@tiflex.co.uk
Web : www.tiflex.co.uk

The information in this document is believed to be correct but does not constitute a specification. It is given in good faith but because of particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or implied with respect to such information. Specifications are subject to change without notice. Statements of operating limits are not an indication that these values can be simultaneously applied.