



# Product Information

## NEBAR GP3

### General Purpose Nitrile

#### Description

A cost effective, medium hardness Nitrile/SBR based cork jointing suitable for a range of industrial applications. Has a degree of oil resistance, but not intended for general sealing of oils and fuels, or at service temperatures above 80°C.

#### Typical Properties

Material tested to procedures as documented in ASTM F104

		Test Procedure
Base elastomer	Nitrile/SBR	
Thickness (mm)	1.5 to 12.5	
Hardness	58 to 68°	ASTM D1415
Minimum tensile strength (MPa)	1.4	ASTM F152
Fluid resistance, volume swells		
ASTM 1 72 hours at 100°C	+11%	ASTM F146
IRM903 72 hours at 100°C	+77%	ASTM F146
FUEL A 22 hours ambient temperatures	+22%	ASTM F146
BS148 Mineral Oil 14 days at 90°C	+82%	ASTM F146
Low temperature flexibility	-25°C	
Maximum operating temperature in fluids	80°C	
Compressibility at 2.8 N/mm <sup>2</sup>	20 to 30%	ASTM F36
Recovery minimum	75%	ASTM F36
Normal sheet size	1.2 x 1.0 (1.5 - 12.5mm) 3.0 x 1.0 (1.5 - 6.0mm)	
Flexibility	5d	ASTM F147

#### Further Information

- Sheets supplied plain and unbranded
- Refer to Technical Services department for advice on specific applications.

# Tiflex

#### Tiflex Limited

Tiflex House, Liskeard, Cornwall, PL14 4NB  
Tel : +44 (0)1579 320808  
E-mail : sales@tiflex.co.uk  
Web : www.tiflex.co.uk

The information in this document is believed to be correct but does not constitute a specification. It is given in good faith but because of particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or implied with respect to such information. Specifications are subject to change without notice. Statements of operating limits are not an indication that these values can be simultaneously applied.