



# Product Information

## NEBAR RED

### High Pressure

**Description** Designed for high pressure applications, mainly in the heavy electrical and switchgear industry, particularly where higher bolt loadings are required than can be tolerated with other Nebar grades. Normally used in mineral oil or Midel 7131 filled transformers.

**Specification Compliance** DTD 900/4911  
AFS 721  
ASTM F104 line call out F224000M2

**Typical Properties** Material tested to procedures as documented in ASTM F104

		Test Procedure
Base elastomer	POLYCHLOROPRENE	
Thickness	0.8 to 13	
Hardness	70 to 85	ASTM D1415
Minimum tensile strength(MPa)	2.35	ASTM F152
Fluid resistance volume swells ASTM F146		
ASTM 1 72 hours at 100°C	-5 to +5%	ASTM F146
IRM903 72 hours at 100°C	+10 to +30%	ASTM F146
FUEL A 22 hours ambient temperatures	0 to +10%	ASTM F146
BS148 Transformer Oil 14 days at 90°C	+10%	ASTM F146
Low temperature flexibility	-30°C	
Maximum operating temperature in fluids	110°C	
Compressibility at 2.8 N/mm <sup>2</sup>	10 to 30%	ASTM F36
Recovery minimum	75%	ASTM F36
Normal sheet size	1.2x1.2 1.2x1.0	
Flexibility as supplied	5d	ASTM F147

**Tiflex Limited**

Tiflex House, Liskeard, Cornwall, PL14 3QG  
Tel : +44 (0)1579 320808  
E-mail : sales@tiflex.co.uk  
Web : www.tiflex.co.uk

The information in this document is believed to be correct but does not constitute a specification. It is given in good faith but because of particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or implied with respect to such information. Specifications are subject to change without notice. Statements of operating limits are not an indication that these values can be simultaneously applied.